

# Product data sheet


**Name of the product:** SPIO@SiO<sub>2</sub>-Epoxy, suspended in deionised water, 5 g/L.

**Guarantee:** 6 months in suspension from manufacture, under the specified storage conditions.

**Product number:** SP2GL18

**Storage:** 4 – 25°C. DO NOT FREEZE.

**Product representation :**



**Usage:** Ensure the nanoparticles are well dispersed in the medium prior to use.

In **suspension**, shake vigorously before use, bath sonication is strongly recommended.

**Product specifications:**

Property	Unit	Specifications	
		Min.	Max.
<i>Characterization technique</i>			
<b>Appearance (Black or brown)</b>			
<i>Visual Inspection</i>	-	-	-
<b>Magnetic</b>			
<i>Test with magnet</i>	-	-	-
<b>Presence of the molecule at the surface</b>			
<i>Infrared analysis (IR)</i>	-	-	-
<b>Loading of -Epoxy at the surface of the nanoparticles</b>	Nb*/nm <sup>2</sup>		
<i>Thermogravimetric analysis (TGA)</i>	Nb*/nm <sup>2</sup>	0.5	8
<b>Phase of SPIO (Magnetite)</b>			
<i>X-ray Diffraction (DRX)</i>	-	-	-
<b>Crystallite size of SPIO</b>			
<i>X-ray Diffraction (DRX)</i>	nm	10	20
<b>Mesh parameter</b>			
<i>X-ray Diffraction (DRX)</i>	Å	8.370	8.390
<b>Oxygen stoichiometry</b>			
<i>X-ray Diffraction (DRX)</i>	-	0	0.111
<b>Fe<sup>2+</sup>/Fe<sup>3+</sup>ratio</b>			
<i>X-ray Diffraction (DRX)</i>	-	0	50
<b>Mean particle size of the SPIO</b>			
<i>Transmission Electron Microscopy (TEM)</i>	nm	10	20
<b>Mean size of the silica layer</b>			
<i>Transmission Electron Microscopy (TEM)</i>	nm	1	10

\*Nb = number of molecules